

Technical Data Sheet

APLSJ01-OR

(Thermoplastic halogen-free fire retardant compound for jacketing of cable)

Description

APLSJ01-OR is a thermoplastic, UV resistance, oil resistance, low smoke, halogen free, flame retardant cable jacketing compound. This product to be used outdoor applications and provides excellent processing characteristics combined with superior level of fire performance, excellent flexibility, and also high mechanical properties.

Specification:

APLSJ-OR meets the applicable requirements given below when processed using extrusion practice and testing procedure:

- IEC 60502-1 type ST8 and IEC 60092-359 type SHF1
- BS 7655:6.1 types LTS1, LTS2, LTS3, LTS4
- DIN VDE 0207, VDE 0250 part 24, Type HM2/HM4
- BS EN 50575

Physical Properties	Standard and Test Method	Unit	Typical value	
Density	IEC 60811-1-3	gr/cm ³	1.45±0.02	
Properties before ageing				
Tensile strength	IEC 60811-1-1	N/mm ²	min 13 min 200	
Elongation at break				
Properties after ageing "7days at 100°C"				
Variation of Tensile strength	IEC 60811-1-2	%	±40 ±40	
Variation of Elongation at break				
Tear strength	BS 6469:99.1	N/mm	10	
Hardness	ASTM D2240	Shore D	52±2	
Melt Flow Index(150 °C/21.6 kg)	ASTM D1238	gr/10min	3	
Heat shock test "1 hr at 150°C"				
Result to be obtained	IEC 60811-3-1	--	No Crack	
Oil immersion – 4 hr at 70°C				
Variation of tensile strength		%	Max 20 Max 40	
Variation of elongation at break				
UV-Exposure for 720 Hours				
Retention Tensile Strength	ASTM G 154	%	86 86	
Retention Elongation				
Hot pressure at 90°C	IEC 60811-3-1	%	30	
Cold Bending test	IEC 60811-1-4	--	Pass	
Cold impact test	IEC 60811-1-4	--	pass	
Burning Properties		Standard and Test Method	Unit	Typical value
Oxygen Index		ASTM D2863	%	32
Acid gas emission	PH	IEC 60754-2	--	>5
	Conductivity		µS/mm	≤10
Halogen acid gas evolution		IEC 60754-1	%	Zero
Smoke Density Rating		ASTM D 2843	%	8
Light Transmission		IEC 61034	%	70
Toxicity Index		NES 713	-	1.7

Processing Condition:

Most halogen free, low smoke materials have a melt viscosity higher than PE/PVC compounds. Such compounds require more power during processing, which leads to a rapid increase in melt temperature, as the screw speed increases.

APLSJ01-OR have been processed on a variety of screw designs, but for optimum output the use of a low compression, low shear screw is recommended. A compression ratio of 1:1.2 is ideal.

As a general guide, typical processing temperature are as follows:

	zone 1	zone 2	zone 3	zone 4	head	die
max (°C)	140	145	150	155	165	175
min (°C)	130	140	145	150	160	160

Color

APLSJ01-OR color is natural. This product is a Colorable Compound with PE/EVA base master batch.

Safety

APLSJ01-OR is classified as no-dangerous material.

Storage

APLSJ01-OR must be stored at ambient conditions which not exceed 30 °C in closed and unbroken packaging in order to avoid exposure to direct sunlight and humidity. The compound should not contact directly with ground. And this product should be avoiding direct exposure to sunlight and weathering.

Packaging

It is available in the form of pellets and supplied in PP laminated bag with a net content of 25 kg.

Technical Service

Abhar Polymer Compounds Technical Service is available to help the customer to choose the best product for his requirements.

Our Technical Service is at your disposal for further information and advice about the start-up and also for any possible necessity during the use of the product.

Disclaimer

The data and numerical results contained in this document are provided for the sake of general information and are given in good faith. They reflect the state of our knowledge at the time of publication. Because the possibilities and application conditions of our product are many and varied, and lie beyond our control, we can in no event be held responsible if all the necessary information on planned applications have not been formally brought to our attention. The information presented here cannot be considered as a suggestion to use our products without taking into account existing patents, or legal provisions or regulations, whether national or local. The purchaser alone assumes the duties of information and advice for the ultimate user. Specifications reported on this datasheet cannot be used as reference values in a technical or sales contract. Abhar Polymer Compounds can in no event be held responsible for a possible failure on the part of the purchaser to respect these regulations, provisions and duties.